THE UNIVERSITY OF MISSOURI

ENGINEERING REPRINT SERIES

Reprint Number 81

Engineering Experiment Station
Columbia, Missouri

HETEROGENEOUS CATALYSIS: Effect of an Alternating Electric Field

Vin-Jang Lee

Assissant Professor of Chemical Engineering
University of Missouri

Reprinted from
Science, April 22, 1966,
Vol. 152, No. 3721, page 514

COLLEGE OF ENGINEERING
THE ENGINEERING EXPERIMENT STATION

The Engineering Experiment Station was organized in 1909 as a part of the College of Engineering. The staff of the Station includes all members of the Faculty of the College of Engineering, together with Research Assistants supported by the Station Funds.

The Station is primarily an engineering research institution engaged in the investigation of fundamental engineering problems of general interest, in the improvement of engineering design, and in the development of new industrial processes.

The Station desires particularly to co-operate with industries of Missouri in the solution of such problems. For this purpose, there is available not only the special equipment belonging to the Station but all of the equipment and facilities of the College of Engineering not in immediate use for class instruction.

Inquiries regarding these matters should be addressed to:

The Director
Engineering Experiment Station
University of Missouri
Columbia, Missouri

Heterogeneous Catalysis: Effect of an Alternating Electric Field

Abstract. Oxidation of carbon monoxide was studied in a static reactor at $123^\circ \pm 1^\circ\text{C}$, with NiO as catalyst. An alternating electric field of about 22,000 volts per centimeter, peak to peak, was applied normal to the catalytic surfaces. The rate of oxidation was thereby enhanced by a factor of 6 at 100 cycles per second, with maximum enhancement at between 100 and 200 cycles per second.

I studied the oxidation of carbon monoxide in a static reactor containing 20 plates of grade-A nickel, 5.08 cm in diameter, oxidized by controlled oxidation to a thickness of about $1\ \mu$ NiO (1). The plates were separated by ceramic spacers—1-mm-thick rings. An a-c electric field of 22,000 volts/cm, peak to peak, was applied between the plates. At frequencies ranging from 50 to 300 cy/sec, the field consisted of a smooth sine wave (Fig. 1). The reactor was totally enclosed in a thermostat controlled at $123^\circ \pm 1^\circ\text{C}$. The re-

actant gases, air and CO, had been dried by passage through drying tubes containing 5A molecular sieve of 30 mesh; they were mixed before entering the reactor. The feed contained 0.028 percent CO_2 and 5.2 percent CO (both by volume); the balance was air. After purge of the reactor for 4 hours at a flow rate of 96 cm/min, the reactant mixture was trapped in the reactor at a pressure of 12.5 cm water above atmospheric.

Compositions of CO and air were determined by measurements of flow rates with two calibrated Matheson-610 flow meters. After a reaction period of from 19 to 68 hours, the resultant gaseous mixture was analyzed for CO_2 content by a gas chromatograph using a silica-gel column; the area under the gas-chromatographic curve was determined with a planimeter, with an estimated possible error of up to 0.01 percent (by volume) CO_2 . Table 1 summarizes the data.

Net conversion of CO to CO_2 was the difference between CO_2 concentrations in the gaseous mixture before and after the reaction (Fig. 2). For the runs without electric field (runs 4/5, 4/6, and 4/12; Table 1), the relation was linear between the amount of CO converted to CO_2 and the resident time of the reactive mixture; this fact may suggest a zero-order reaction. However, since the change in CO concentration was relatively small, the order of the reaction cannot be asserted with certainty.

The net conversion to CO_2 during 19 hours in the reactor is plotted in Fig. 2 as a function of the a-c field frequency at a constant peak-to-peak field of 22,000 volts/cm. Apart from high-frequency distortions at 400 cy/sec, the field was a smooth sine wave. The enhancement of the rate of oxidation of CO does not reflect the heating effects of the a-c circuit because the capacitor

Fig. 1. Oscilloscope display of the sinusoidal electric field applied between the NiO catalytic surfaces. Scales: horizontal, 0.5 millisecond per division; vertical, 500 volts per division.

Fig. 2. Net increment (percentage by volume) of CO_2 after 19 hours in the reactor at $123^\circ \pm 1^\circ\text{C}$ and at a pressure of 12.5 cm water above atmospheric. Open circle, with no field applied on the NiO catalyst; solid circles, with sinusoidal electric field applied. Cps, cycles per second.

plates, serving as catalyst, were the only part of the circuit in the reactor. *A fortiori*, the temperature of the reactor was automatically controlled at $123^\circ \pm 1^\circ\text{C}$ during all experiments.

The fact that the rate of reaction was maximum at between 100 and 200 cy/sec may imply that the resident time of the adsorbed species is of the order of 5 to 10 msec. The nature of the adsorbate and the reaction mechanism remain to be determined.

VIN-JANG LEE

Department of Chemical Engineering,
University of Missouri, Columbia

References and Notes

1. O. Kubaschewski and B. E. Hopkins, *Oxidation of Metal* (Academic Press, New York, 1962), pp. 243-4.
2. I thank R. G. Schultz, M. A. Gilleo, and G. E. Barker of the Monsanto Co., St. Louis, Missouri, for their participation.

Table 1. Oxidations of CO to CO_2 during eight runs. PP, peak to peak.

Run	Duration (hr)	Field, PP (volts/cm)	Frequency (cy/sec)	CO_2 (vol %)	
				In residue	Net conversion
4/5	67	none		0.168	0.140
4/6	19	none		.060	.032
4/7	19	22,000	50	.195	.167
4/8	19	22,000	100	.230	.202
4/9	19	22,000	200	.215	.186
4/12	68	none		.175	.147
4/13	19	22,000	300	.138	.110
4/14	19	22,000	400	.138*	.110

* Wave form contained high-frequency distortions.

PUBLICATIONS OF THE ENGINEERING REPRINT SERIES

Copies of publications may be secured from the Director of the Engineering Experiment Station, University of Missouri. Single copies may be obtained free unless otherwise indicated until the supply is exhausted. Requests for additional copies will be considered upon further inquiry.

Reprint No.

68. A Method of Data List Processing with Application to EEG Analysis by C. M. Philpott, Control Data Corporation, St. Paul, Minnesota, and G. B. Lago, Professor of Electrical Engineering, University of Missouri. Reprinted from Communications of the ACM, Volume 8, Number 5, May, 1965.
69. Method for Obtaining the Trees of a v Vertex Complete Graph from the Trees of a $v-1$ Vertex Complete Graph by G. W. Zobrist, Assistant Professor of Electrical Engineering, University of Missouri, and G. V. Lago, Professor of Electrical Engineering, University of Missouri. Reprinted from the Matrix and Tensor Quarterly, Volume 15, Number 3, March, 1965.
70. Treatment of Livestock Waste—A Laboratory Study by E. A. Jeffrey, W. C. Blackmann, Jr., and Ralph Ricketts. Reprinted from Transactions of the ASAE, Volume 8, Number 1.
71. The Electronic Position Indicator by Richard P. Covert, Associate Professor of Industrial Engineering, University of Missouri. Reprinted from The Journal of Industrial Engineering, Volume XVI, No. 4, July-August, 1965, pages 255-259.
72. The Reflected Impedance of a Circular Coil in the Proximity of a Semi-Infinite Medium by David H. S. Cheng. Reprinted from IEEE Transactions on Instrumentation and Measurement, Volume IM-14, Number 3, September, 1965.
73. Irrotational Flow Over Spillways of Finite Height by John J. Cassidy, Associate Professor of Civil Engineering, University of Missouri. Reprinted from Journal of the Engineering Mechanics Division, Proceedings of the American Society of Civil Engineers, Volume 91, Number EM6, December, 1965.
74. Experimental Investigation of a Magnetically Balanced Arc in a Transverse Argon Flow by T. W. Myers, Visiting Research Associate, Thermo-Mechanics Research Laboratory, Wright-Patterson AFB, Ohio, C. N. McKinnon, Instructor of Mechanical Engineering, University of Missouri, and J. C. Lysen, Associate Professor of Mechanical Engineering, University of Missouri. Reprinted from Journal of Engineering for Power, January, 1966.
75. A Study of the Effects of Paced Audio-Rhythm on Repetitive Motion by John A. Conte, Undergraduate Industrial Engineer, University of Missouri. Reprinted from The Journal of Industrial Engineering, Volume XVII, Number 3, 1966.
76. Measured and Computed Stresses in Three Castellated Beams by Richard T. Douty, Associate Professor of Civil Engineering and James W. Baldwin, Professor of Civil Engineering, University of Missouri. Reprinted from AISC Journal, January, 1966.
77. A Method of Obtaining a Uniform Electric Field by A. V. Dralle and D. L. Waidelich. Reprinted from 1966 IEEE International Convention Record, Part 7.
78. The Use of the Flux Plot in Traffic Control by Robert J. Wheeler, Associate Professor of Civil Engineering and Elmer M. Tory, Associate Professor Mathematics, Mount Allison University. Reprinted from the Traffic Quarterly, July 1965.
79. A Statistical Definition of Perfect Mixtures of Solids of Different Sizes by Kun Sup Hyun, Graduate Student in Chemical Engineering, and L. E. Marc De Chazal, Professor of Nuclear and Chemical Engineering, University of Missouri. Reprinted from I & EC Process Design and Development, Vol. 5, April 1966.
80. A Qualitative and Quantitative Measure of Aufwuchs Production, by Darrell L. King, Assistant Professor of Civil Engineering, University of Missouri and Robert C. Ball, Professor of Fisheries and Wildlife, Michigan State University. Reprinted from Trans. Amer. Micros. Soc. 85 (2): 232-240. 1966.
81. Heterogeneous Catalysis: Effect of an Alternating Electric Field by Vin-Jang Lee, Assistant Professor of Chemical Engineering, University of Missouri. Reprinted from Science, April 22, 1966, Vol. 152, No. 3721, page 514.

University of Missouri Libraries
University of Missouri

MU Engineering Experiment Station Series

Local Identifier Leel966

Capture information

Date captured 2018 May

Scanner manufacturer Ricoh
Scanner model MP C4503
Scanning software
Optical resolution 600 dpi
Color settings Color, 24 bit
File types Tiff

Source information

Format Book
Content type Text
Notes Digitized duplicate copy not retained in collection.

Derivatives - Access copy

Compression LZW
Editing software Adobe Photoshop
Resolution 600 dpi
Color Color, 24 bit
File types Tiffs converted to pdf
Notes Greyscale pages cropped and canvassed. Noise removed from
 background and text darkened.
 Color pages cropped.